

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

Group Number Assessment

(In accordance with AS 5637.1-2015)


This is to confirm that the product as described below has been tested by AWTA Product Testing.

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

Test Sponsor :	Atlas Steels Alfacade	Test Number :	25-001892
	131 Calarco	Issue Date :	20/05/2025
	Derrimut VIC 3030	Print Date :	21/05/2025

Sponsor Product :	Clients Ref :	"AlFacade"
	Coated Aluminium Panel	
	Colour :	Cream
	End Use :	Cladding
	Nominal Composition :	Solid Aluminium, PVDF coating
	Nominal Mass per Unit Area/Density :	27kg/m3
	Nominal Thickness :	Approx: 3mm



77179

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. Its transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing.

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

Test Sponsor : Atlas Steels Alfacade
131 Calarco
Derrimut VIC 3030

Test Number : 25-001892
Issue Date : 20/05/2025
Print Date : 21/05/2025

Product Group Number Classification :

1

Average Specific Extinction Area :

43.5 m²/kg



Chris Campbell
Client Relations Manager

77179

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. Its transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, its disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.